

SPECIFICATION	DOC. NO	SP/6/204/1048
	REVISION	1
	DATE OF ISSUE	21/07/2016
	PAGE	1 OF 1
TITLE: CARBONLESS PAPER (R) 53, 55 & 60 GSM – EUROSTAR		

NO.	PARAMETER	UNIT		VALUE						TEST METHOD
				CB 55	CB 60	CFB 53	CFB 60	CF 55	CF 60	
1.	Basis Weight	g/m ²		52 – 56	60 ± 2	53 ± 2	60 ± 2	52 – 56	60 ± 2	<u>ISO 536 : 2012</u>
2.	Thickness	µm		77 ± 3	84 ± 3	73 ± 3	82 ± 3	69 ± 3	77 ± 2	<u>ISO 534 : 2011</u>
3.	Bentsen Roughness	ml/min	TS	Max. 180	Max. 180	Max. 150	Max. 190	Max. 150	Max. 150	<u>ISO 8791-2:2013</u>
			BS	Max. 500	Max. 500	Max. 500	Max. 500	Max. 150	Max. 150	
4.	Smudging	%		-	-	Max. 7	Max. 7	-	-	-
5.	Copy Intensity	%	2 nd	Min. 29	Min. 29	Min. 29	Min. 29	Min. 29	Min. 29	-
			5 th	-	-	Min. 27	Min. 27	-	-	
			6 th	-	-	Min. 26	Min. 26	Min. 26	Min. 26	

Note : TS = Top Side
BS = Back Side
Printer type for Intensity : EPSON LQ-2180 Standard Resolution 180 x 180
All data above are adopted from existing specification of Impression 2000

Prepared By :

Sec. Head of QC
Date : 21/7/2016

Head of QC (Laboratory)
Date : 21/7/2016

Approved By :

Production Manager
Date : 21/7/2016

Head of Tech. Division
Date : 21/7/2016